


TEST REPORT

Technical Report: (9320)303-1134

Page 1 of 4 November 04, 2020



Bureau Veritas Consumer Products Services (Guangzhou) Co., Ltd

(Guangzhou, Co., Etc.) No. 183, Shinan Road, Meilin Plaza, Dongchong, Nansha, Guangzhou, Guangdong Province, China 511453 Tel: (86) 20 2290 2088 Fax: (86) 20 3490 9303 Email: BVCPS_pyinfo@cn.bureauveritas.com Website: cps.bureauveritas.com This report is governed by, and incorporates by reference, CPS Conditions of Service as posted at the date of issuance of this report at http://www.bureauveritas.com/home/about-us/our-business/cps/about-us/terms-conditions/and is intended for your exclusive use. Any copying or replication of this report to or for any other person or entity, or use of our name or trademark, is permitted only with our prior written permission. This report sets forth our findings solely with respect to the test samples identified herein. The results set forth in this report are not indicative representative of the quality or characteristics of the lot from which a test sample was taken or any similar or identical product unless specifically and expressly noted. Our report includes all of the tests requested by you and the results thereof based upon the information that you provided to us. Measurement uncertainty all provided, however, that such notice shall be in writing and shall specifically address the issue you wish to raise such issue within the prescribed time shall constitute you unqualified acceptance of the completeness of this report, the tests conducted and the correctness of the report contents.



TEST REPORT

TO: MOSAROMA INT'L CO LTD 5/F TERN CENTRE TOWER 2 251 QUEEN'S ROAD

HONG KONG

ATTN: SHI,

LAB NO.: (9320)303-1134

FORM NO.:

DATE IN: Oct 29, 2020 **DATE OUT:** Nov 04, 2020

NO. OF WORKING DAYS: 5

PAGE 2 OF 4

OVERALL RATING	
PASS FAIL DATA	x

Vendor:	/	Agent:	/
Fabric Supplier/Mill:	/	Factory/Manufacturer:	/
P.O. No.:	/	Style No.:	15243104/ 15243071
Sample Description:	100% SOLUTION-DYED BLEND	Style Description:	/
	SPUN (AXVISION)		
Color:	GREY (A-B: SEE PHOTO)	Country of Origin:	/
Claimed Fabric Weight:	/	Claimed Fabric Count:	/
Yarn Size:	/	Submitted Size:	/
Size Range:	/	FPU No.:	/
GPU No.:	/	End Use:	OUTDOOR CUSHION/
			PILLOW/
			UPHOLSTERY
SKU:	/	Age Group:	/

Product Category	FABRIC
Test Requested	SEE TEST PROPERTY
Previous Report No.	

Submitted Fiber	100% SOLUTION-DYED BLEND SPUN
Content	
Actual Fiber Content	
Suggested Fiber	
Content	
Submitted Care	/
Instruction(s)	
Client Expected Care	
Instruction	
Suggested Care	
Instruction(s)	

TEST PROPERTY	PASS	FAIL	DATA	COMMENTS
PILLING RESISTANCE: MARTINDALE			Х	
PRESSURE TESTER METHOD				

TECHNICAL QUESTIONS

(86)20-22902088 bvcps_pyinfo@cn.bureauveritas.com

GENERAL INFORMATION

(86)20-22902088 bvcps_pyinfo@cn.bureauveritas.com

SIGNATURES

Bureau Veritas Consumer Products Services (Guangzhou) Co., Ltd

Apollo Luo Senior Manager

TEST RESULTS

TEST PROPER	rv	TES	T RESULTS		REQUIREMENTS
IEST PROPER	<u> </u>				REQUIREMENTS
PILLING RESISTANCE:	MARTINDALE	PRESSURE	TESTER MET	'HOD (ASTM	
D4970-16E3)					
A					
5000 CYCLES					
,		1	2	3	,
PILLING (GRADE)		4.5	4.5	4.5	/
DILLING (CDADE)		4		Avg. 4.5	/
PILLING (GRADE)		4.5		4.5	/
10000 CYCLES					
10000 CICEED		1	2	3	
PILLING (GRADE)		4.0	4.0	4.0	/
,		4		Avg.	
PILLING (GRADE)		4.0		4.0	/
В					
5000 CYCLES				•	
		1	2	3	,
PILLING (GRADE)		4.5 4	4.5	4.5	/
PILLING (GRADE)		4.5		Avg. 4.5	/
TIBLING (GIAIDE)		4.5		4.5	/
10000 CYCLES					
		1	2	3	
PILLING (GRADE)		4.0	4.0	4.0	/
		4		Avg.	
PILLING (GRADE)		4.0		4.0	/