



TEST REPORT

TO: CONFER FRAGRANT CO., LTD.

LAB NO.: (6215) 211-0074
DATE IN: JULY 30, 2015
DATE OUT: AUG. 10, 2015
MOD. DATE: -
PAGE: 1 OF 4
WORKING DAYS: 7

PURPOSE OF TEST: To evaluate the submitted sample in the test requested by the client only.

OVERALL RATING: DATA

SAMPLE DESCRIPTION:

Item Description:	#4876 (1PC WITHOUT PACKAGE)
Style No.:	-
P.O.No.:	-
Sources/Vendor:	-
Manufacturer:	-
Orig. Of Country:	-
Size:	-
Color:	-

COMMENTS:

Please see attached Test Results for detailed test data on all requested test.

SUMMARY OF TEST RESULTS

TEST RESULTS	PASS	FAIL	
FABRIC STRENGTH			See Test Result

Remark: BVCPS Contact information for this report.

Technical questions:

Primary Contact: Andy Lin, Tel: 886-2-2895-3666#280, email: andy.lin@tw.bureauveritas.com

Back-up Contact: Chad Hsieh, Tel: 886-2-2895-3666#302, email: chad.hsieh@tw.bureauveritas.com

Concerns regarding billing:

Primary Contact: Judy Chan, Tel: 886-2-2895-3666#304, email: judy.chan@tw.bureauveritas.com

Back-up Contact: Iris Yang, Tel: 886-2-22895-3666#310, email: iris.yang@tw.bureauveritas.com

**BUREAU VERITAS CONSUMER PRODUCTS SERVICES (H.K.) LIMITED,
TAIWAN BRANCH**



**CHAD HSIEH
HARDLINE OPERATION MANAGER**

REMARKS:

1. This report is intended for your exclusive use. Any copying or replication of this report to or for any other person or entity, or use of our name or trademark, is permitted only with our written permission.
2. Our report is limited to the test samples identified herein. The results set forth in this report are not necessarily indicative or representative of the statistical quality or characteristics of the lot from which a test sample was taken or any similar or identical product unless specifically and expressly noted.
3. Our report includes all the tests requested by you and the results thereof. You shall have thirty days from receipt of this report to request additional testing of the samples or to notify us of any errors or omissions relating to our report; provided, however, such notice shall be in writing and shall specifically address the issue you wish to raise. A failure to raise such issue within the prescribed time shall constitute your unqualified acceptance of the completeness of this report, the tests conducted and the correctness of the report contents.

TEST RESULT

FABRIC STRENGTH (ASTM D5034, 1-INCH G-E, INSTRON, SPEED 12
IN/MIN)

WARP(LBS/IN)	429.0
WEFT(LBS/IN)	220.8

