




**BUREAU
VERITAS**

TEST REPORT

Technical Report: (9322)137-2573REVISED

Page 1 of 4
June 9, 2022



Report Number
(9322)137-2573



**BUREAU
VERITAS**

TEST REPORT

**TO : MOSAROMA INT'L CO LTD
5/F TERN CENTRE TOWER 2
251 QUEEN'S ROAD
HONG KONG**

ATTN : SHI ,

LAB NO.: (9322)137-2573
REVISED
FORM NO.: /
DATE IN: May 17, 2022
DATE OUT: Jun 01, 2022
NO. OF WORKING DAYS: /
REVISED DATE: Jun 09, 2022
PAGE 2 OF 4

OVERALL RATING	
PASS	_____
FAIL	_____
DATA	_____X_____

Vendor:	/	Agent:	/
Fabric Supplier/Mill:	/	Factory/Manufacturer:	/
P.O. No.:	/	Style No.:	13737324
Sample Description:	100% SOLUTION-DYED BLEND SPUN (AXVISION)	Style Description:	/
Color:	WHITE	Country of Origin:	/
Claimed Fabric Weight:	/	Claimed Fabric Count:	/
Yarn Size:	/	Submitted Size:	/
Size Range:	/	FPU No.:	/
GPU No.:	/	End Use:	OUTDOOR CUSHION, PILLOW, UPHOLSTERY
SKU:	/	Age Group:	/

Product Category	FABRIC
Test Requested	SEE TEST PROPERTY
Previous Report No.	/

Submitted Fiber Content	100% SOLUTION-DYED BLEND SPUN
Actual Fiber Content	/
Suggested Fiber Content	/
Submitted Care Instruction(s)	/
Client Expected Care Instruction	/
Suggested Care Instruction(s)	/



BUREAU
VERITAS

TEST PROPERTY	PASS	FAIL	DATA	COMMENTS
PILLING RESISTANCE: MARTINDALE PRESSURE TESTER METHOD			X	
ABRASION RESISTANCE OF TEXTILE FABRICS			X	

TECHNICAL QUESTIONS (86)20-22902088
bvcps_pyinfo@cn.bureauveritas.com

GENERAL INFORMATION (86)20-22902088
bvcps_pyinfo@cn.bureauveritas.com

SIGNATURES Bureau Veritas Consumer Products Services (Guangzhou) Co., Ltd

Quan Peng
Operation Manager



<u>TEST PROPERTY</u>	<u>TEST RESULTS</u>			<u>REQUIREMENTS</u>
<u>PILLING RESISTANCE: MARTINDALE PRESSURE TESTER METHOD</u> (ASTM D4970-16E3, PHOTOGRAPHIC RATING STANDARD AT 10000 MOVEMENTS)				
PILLING (GRADE)	1 3.5	2 3.5	3 3.5	/
PILLING (GRADE)	4 3.5		Avg. 3.5	/
<u>ABRASION RESISTANCE OF TEXTILE FABRICS</u> (ASTM D4157)				
		WARP:>20000.0 CYCLES, WEFT:>20000.0 CYCLES		/