


TEST REPORT

Technical Report: (9318)215-0963

> Page 1 of 4 November 07, 2018



(Guangzhou) Co., Ltd No. 183, Shinan Road, Meilin Plaza, Dongchong, Nansha, Guangzhou, Guangdong Province, China 511453 Tel: (86) 20 2290 2088 Fax: (86) 20 3490 9303 Email: BVCPS_pyinfo@cn.bureauveritas.com Website: cps.bureauveritas.com



TEST REPORT

TO: MOSAROMA INT'L CO LTD 7/F., BLISSFUL BUILDING

243-247 DES VOEUX ROAD CENTRAL

HONG KONG ISLAND,

HONG KONG

LAB NO.: (9318)215-0963

FORM NO.:

DATE IN: Aug 03, 2018 **DATE OUT:** Nov 07, 2018

NO. OF WORKING DAYS: /

PAGE 2 OF 4

A	TT	Ν	:	W	/EN	ĪΓ	A	0	SH	11
---	----	---	---	---	-----	----	---	---	----	----

OVERALL RATING	
PASS FAIL	
DATA	Х

Vendor:	/	Agent:	/
Fabric Supplier/Mill:	/	Factory/Manufacturer:	/
P.O. No.:	/	Style No.:	15225022
Sample Description:	100% SOLUTION-DYED POLYESTER	Style Description:	/
Color:	GREEN	Country of Origin:	/
Claimed Fabric Weight:	/	Claimed Fabric Count:	/
Yarn Size:	/	Submitted Size:	/
Size Range:	/	FPU No.:	/
GPU No.:	/	End Use:	CUSHION, PILLOW
SKU:	/	Age Group:	/

Product Category	FABRIC
Test Requested	SEE TEST PROPERTY
Previous Report No.	

Submitted Fiber	100% POLYESTER
Content	
Actual Fiber Content	1
Suggested Fiber	/
Content	
Submitted Care	/
Instruction(s)	
Client Expected Care	/
Instruction	
Suggested Care	/
Instruction(s)	



TEST PROPERTY	PASS	FAIL	DATA	COMMENTS
COLORFASTNESS TO LIGHT			X	

TECHNICAL QUESTIONS

SIGNATURES

Bureau Veritas Consumer Products

Services (Guangzhou) Co., Ltd

(86)20-22902088

CPSCSEnquiry.PY@cn.bureauveritas.com

GENERAL INFORMATION

Joeie Tsang General Manager



TEST RESULTS

	1151 11250115				
TEST PROPERTY		REQUIREMENTS			
COLORFASTNESS TO LIGHT (AA XENON-ARC LAMP, 800/1000/	TCC 16.3-14, OPTION 3, WATER COOLED 1200 AFU)				
COLOR CHANGE (800 AFU) COLOR CHANGE (1000 AFU)	4.0 3.5	/ /			
COLOR CHANGE (1200 AFU)	3.0	/			

COLORFASTNESS RATING COLOR CHANGE

- 5 NEGLIGIBLE OR NO CHANGE
- 4 SLIGHTLY CHANGED
- 3 NOTICEABLY CHANGED
- 2 CONSIDERABLY CHANGED
- 1 MUCH CHANGED

COLORFASTNESS RATING COLOR STAIN SELF STAINING

- 5 NEGLIGIBLE OR NO STAINING
- 4 SLIGHTLY STAINED
- 3 NOTICEABLY STAINED
- 2 CONSIDERABLY STAINED
- 1 HEAVILY STAINED