



**BUREAU
VERITAS**

TEST REPORT

Technical Report: (9322)355-1387 **REVISED**

Page 1 of 4
March 09, 2023



Report Number
(9322)355-1387



**BUREAU
VERITAS**

TEST REPORT

TO : TRAMEX TRADING CO LTD
FLAT/ROOM 4304, 43/F
CHINA RESOURCES BUILDING 26
HARBOUR ROAD
WANCHAI
HONGKONG ISLAND,
HONG KONG

LAB NO.: (9322)355-1387
REVISÉ
FORM NO.: /
DATE IN: Dec 21, 2022
DATE OUT: Mar 09, 2023
REVISÉ DATE: Apr 07, 2023
NO. OF WORKING DAYS: /
PAGE 2 OF 4

ATTN : ALEXANDRE TELLINGS

<u>OVERALL RATING</u>	
PASS	_____
FAIL	_____
DATA	_____X_____

Vendor:	/	Agent:	/
Fabric Supplier/Mill:	/	Factory/Manufacturer:	/
P.O. No.:	/	Style No.:	NOVASUN
Sample Description:	100% SOLUTION-DYED POLYESTER	Style Description:	/
Color:	NOVASUN	Country of Origin:	/
Claimed Fabric Weight:	/	Claimed Fabric Count:	/
Yarn Size:	/	Submitted Size:	/
Size Range:	/	FPU No.:	/
GPU No.:	/	End Use:	UMBRELLAS, CUSHIONS, SOFAS
SKU:	/	Age Group:	/

Product Category	FABRIC
Test Requested	SEE TEST PROPERTY
Previous Report No.	/

Submitted Fiber Content	100% POLYESTER
Actual Fiber Content	/
Suggested Fiber Content	/
Submitted Care Instruction(s)	/
Client Expected Care Instruction	/
Suggested Care Instruction(s)	/



**BUREAU
VERITAS**

TEST PROPERTY	PASS	FAIL	DATA	COMMENTS
COLORFASTNESS TO LIGHT			X	SEE RESULT

**TECHNICAL
QUESTIONS**

(86)20-22902088
bvcps_pyinfo@cn.bureauveritas.com

**GENERAL
INFORMATION**

(86)20-22902088
bvcps_pyinfo@cn.bureauveritas.com

SIGNATURES

Bureau Veritas Consumer Products Services
(Guangzhou) Co., Ltd

Quan Peng
Operation Manager



<u>TEST PROPERTY</u>	<u>TEST RESULTS</u>	<u>REQUIREMENTS</u>
----------------------	---------------------	---------------------

COLORFASTNESS TO LIGHT (AATCC 16.3-20, OPTION 3, WATER COOLED XENON-ARC LAMP, 1000 & 1100 & 1200 & 1300 & 1400 & 1500 AFU)

COLOR CHANGE (1000 AFU)	3.5	/
COLOR CHANGE (1100 AFU)	3.0	/
COLOR CHANGE (1200 AFU)	3.0	/
COLOR CHANGE (1300 AFU)	3.0	/
COLOR CHANGE (1400 AFU)	2.5	/
COLOR CHANGE (1500 AFU)	2.5	/

**COLORFASTNESS RATING
COLOR CHANGE**

- 5 NEGLIGIBLE OR NO CHANGE
- 4 SLIGHTLY CHANGED
- 3 NOTICEABLY CHANGED
- 2 CONSIDERABLY CHANGED
- 1 MUCH CHANGED

**COLORFASTNESS RATING
COLOR STAIN
SELF STAINING**

- 5 NEGLIGIBLE OR NO STAINING
- 4 SLIGHTLY STAINED
- 3 NOTICEABLY STAINED
- 2 CONSIDERABLY STAINED
- 1 HEAVILY STAINED

END OF REPORT