

## **TEST REPORT**

**Technical Report:** (9323)130-1751

Page 1 of 4 May 12, 2023



Bureau Veritas Consumer Products Services (Guangzhou) Co., Ltd

No. 183, Shinan Road, Meilin Plaza, Dongchong, Nansha, Guangzhou, Guangdong Province, China 511453

Tel: (86) 20 2290 2088 Fax: (86) 20 3490 9303 Email: BVCPS\_pyinfo@cn.bureauveritas.com Website: cps.bureauveritas.com This report is governed by, and incorporates by reference, the Conditions of Testing as posted at the date of issuance of this report at <a href="http://www.bure.auveritas.com/home/about-us/our-business/cps/about-us/ferms-conditions/">http://www.bure.auveritas.com/home/about-us/our-business/cps/about-us/ferms-conditions/</a> and is intended for your exclusive use. Any copying or replication of this report to or for any other person or entity, or use of our name or trademants, is permitted only with our prior written permission. This report sets forth our findings soled with respect to the lest samples identified herein. The results set forth in this report are not indicative or representative of the quality or characteristics of the lot from which a test sample was taken or any similar or identical product unless specifically and expressly noted. Our report includes all of the tests requested by you and the results thereof based upon the information that you provided to us. Measurement uncertainty into account, unless otherwise requested in writing. You have 60 days from date of issuance of this report to notify us of any material error or omission caused by our negligence or if you require measurement uncertainty; provided, however, that such notice shall be in writing and shall specifically address the issue you wish to raise. A failure to raise such issue within the prescribed time shall constitute you unqualified acceptance of the completeness of this report, the tests conducted and the correctness of the report contents.



ATTN: SHI,

# **TEST REPORT**

TO: MOSAROMA INT'L CO LTD 7F, BLISSFUL BUILDING 243-247 DES VOEUX ROAD

CENTRAL

HONG KONG ISLAND,

**HONG KONG** 

**LAB NO.:** (9323)130-1751

FORM NO.:

**DATE IN:** May 10, 2023 **DATE OUT:** May 12, 2023

NO. OF WORKING DAYS: 3

PAGE 2 OF 4

·		
	OVERALL RATING	
	PASS FAIL	
	DATA	X

Vendor:	/	Agent:	/
Fabric Supplier/Mill:	/	Factory/Manufacturer:	/
P.O. No.:	/	Style No.:	15226853
Sample Description:	100% SOLUTION-DYED BLEND SPUN(AXVISION)	Style Description:	/
Color:	BEIGE	Country of Origin:	/
Claimed Fabric Weight:	/	Claimed Fabric Count:	/
Yarn Size:	/	Submitted Size:	/
Size Range:	/	FPU No.:	/
GPU No.:	1	End Use:	OUTDOOR CUSHION/PILLOW/UP HOISTERY
SKU:	/	Age Group:	/

Product Category	FABRIC
Test Requested	SEE TEST PROPERTY
Previous Report No.	1

Submitted Fiber	100% SOLUTION-DYED BLEND SPUN
Content	
Actual Fiber Content	1
Suggested Fiber	/
Content	
Submitted Care	/
Instruction(s)	
Client Expected Care	/
Instruction	
Suggested Care	/
Instruction(s)	



TEST PROPERTY	PASS	FAIL	DATA	COMMENTS
RESISTANCE TO YARN SLIPPAGE IN			X	
WOVEN UPHOLSTERY FABRICS				

**TECHNICAL QUESTIONS**  (86)20-22902088

bvcps\_pyinfo@cn.bureauveritas.com

**GENERAL** INFORMATION

(86)20-22902088 bvcps\_pyinfo@cn.bureauveritas.com

SIGNATURES Bureau Veritas Consumer Products Services (Guangzhou) Co., Ltd

Quan Peng

Operation Manager



#### TEST RESULTS

## TEST PROPERTY REQUIREMENTS

### RESISTANCE TO YARN SLIPPAGE IN WOVEN UPHOLSTERY FABRICS (ASTM

D4034, 1-INCH, G-E, INSTRON, SPEED 12 IN/MIN, 7.0 +/- 0.5 STITCHES PER INCH)

SEAM PARALLEL TO WARP - @0.25" NSS

YARN SLIPPAGE (LBF.)

SEAM PARALLEL TO WARP - SEAM 80.5

STRENGTH (LBF.)

SEAM PARALLEL TO WARP - MODE OF STB

FAILURE (LBF.)

SEAM PARALLEL TO WEFT - @0.25" NSS

YARN SLIPPAGE (LBF.)

SEAM PARALLEL TO WEFT - SEAM 90.9

STRENGTH (LBF.)

SEAM PARALLEL TO WEFT - MODE OF STB

FAILURE (LBF.)