




**BUREAU
VERITAS**

TEST REPORT

Technical Report: (9326)099-1621

Page 1 of 4
April 14, 2026



Report Number
(9326)099-1621



**BUREAU
VERITAS**

TEST REPORT

**TO : MOSAROMA INT'L CO LTD
7/F., BLISSFUL BUILDING
243-247 DES VOEUX ROAD CENTRAL
HONG KONG ISLAND,
HONG KONG**

LAB NO.: (9326)099-1621
FORM NO.: /
DATE IN: Apr 09, 2026
DATE OUT: Apr 14, 2026
NO. OF WORKING DAYS: 4
PAGE 2 OF 4

ATTN : LEO

<u>OVERALL RATING</u>	
PASS	_____
FAIL	_____
DATA	_____ X _____

Vendor:	/	Agent:	/
Fabric Supplier/Mill:	/	Factory/Manufacturer:	/
P.O. No.:	/	Style No.:	15225037
Sample Description:	100% SOLUTION- DYED POLYESTER	Style Description:	/
Color:	BEIGE	Country of Origin:	/
Claimed Fabric Weight:	/	Claimed Fabric Count:	/
Yarn Size:	/	Submitted Size:	/
Size Range:	/	FPU No.:	/
GPU No.:	/	End Use:	OUTDOOR CUSHION/PILLOW/UP HOLSTERY
SKU:	/	Age Group:	/

Product Category	FABRIC
Test Requested	SEE TEST PROPERTY
Previous Report No.	/

Submitted Fiber Content	100% SOLUTION-DYED POLYESTER
Actual Fiber Content	/
Suggested Fiber Content	/
Submitted Care Instruction(s)	/
Client Expected Care Instruction	/
Suggested Care Instruction(s)	/



**BUREAU
VERITAS**

TEST PROPERTY	PASS	FAIL	DATA	COMMENTS
ABRASION RESISTANCE OF FABRICS BY MARTINDALE METHOD: SPECIMEN BREAKDOWN			X	SEE RESULT

**TECHNICAL
QUESTIONS** (86)20-22902088
bvcps_pyinfo@cn.bureauveritas.com

**GENERAL
INFORMATION** (86)20-22902088
bvcps_pyinfo@cn.bureauveritas.com

SIGNATURES Bureau Veritas Consumer Products Services
(Guangzhou) Co., Ltd

Quan Peng
Operation Manager



<u>TEST PROPERTY</u>	<u>TEST RESULTS</u>	<u>REQUIREMENTS</u>
ABRASION RESISTANCE OF FABRICS BY MARTINDALE METHOD: SPECIMEN BREAKDOWN (ISO 12947-2:2016 / BS EN ISO 12947-2:2016/ DIN EN ISO 12947-2:2017 / NF EN ISO 12947-2:2017, PRESSURE USED: 12 KPA)		
LOWEST INDIVIDUAL TEST RESULT (RUBS)	50000.0	/

-END OF REPORT-